


# DATA SHEET

# AR+AR SPECTRUM

Batch No. : A050607b3

Spectrum :



Optical Spec.		Coating Result
Wave Length (nm)	Transmission (%)	Transmission (%)
420~680nm	Tavg=97% ; Tabs>95%	Tavg=98.08% ; Tabs>97.38%

Wave.	T%	Wave.	T%	Wave.	T%	Wave.	T%	Wave.	T%	Wave.	T%	Wave.	T%	Wave.	T%
800	93.52	735	97.06	670	98.35	605	98.15	540	97.92	475	98.74	410	97.93	345	69.08
795	93.84	730	97.26	665	98.28	600	97.89	535	97.87	470	98.59	405	98.02	340	63.34
790	94.04	725	97.44	660	98.17	595	97.87	530	97.79	465	98.51	400	98.19	335	57.66
785	94.4	720	97.72	655	98.38	590	97.73	525	98.28	460	98.38	395	98.03	330	52.75
780	94.7	715	97.69	650	98.32	585	97.6	520	98.19	455	98.24	390	97.66	325	48.07
775	95	710	97.81	645	98.32	580	97.66	515	98.42	450	98	385	97	320	44.57
770	95.44	705	97.98	640	98.33	575	97.87	510	98.53	445	97.99	380	96.11	315	41.95
765	95.68	700	98.12	635	98.29	570	97.98	505	98.41	440	97.92	375	94.68	310	40.44
760	95.87	695	98.03	630	98.22	565	97.79	500	98.57	435	97.59	370	92.07	305	39.99
755	96.13	690	98.23	625	97.98	560	97.47	495	98.85	430	97.67	365	89.19	300	39.73
750	96.66	685	98.21	620	98.22	555	97.76	490	98.66	425	97.71	360	84.99		
745	96.66	680	98.27	615	98.02	550	97.81	485	98.71	420	97.89	355	79.71		
740	97	675	98.34	610	98.02	545	97.65	480	98.69	415	98.08	350	74.56		

GM-2P-8204-00