


DATA SHEET

SCHOTT VG9

Optical properties	
Reflection factor	
$P_d = 0,911$	
Spectral values guaranteed	
τ_i (450 nm)	$\leq 0,21$
τ_i (514 nm)	$\geq 0,67$
τ_i (633 nm)	$\leq 0,15$
τ_i (725 nm)	$\leq 0,07$
τ_i (1060 nm)	$\leq 0,18$
Refractive indices	
n_d (587,6 nm) = 1,55	
Sellmeier coefficients	
on request	
Internal quality	
Bubble class	1


Mechanical properties	
Reference thickness	
$d = 1,00$ mm	
Density	
$\rho = 2,87$ g/cm ³	
Knoop hardness	
HK[0.1/20] = 449	
Thermal properties	
Transformation temperature	
$T_g = 451$ °C	
Thermal expansion in $10^{-6}/K$	
α (-30°C/+70°C)	= 9,2
α (20°C/300°C)	= 10,6
Chemical properties	
Chemical resistance	
FR class	= 0
SR class	= 1
AR class	= 1

Colorimetric properties				
	1 mm	2 mm	3 mm	
Illuminant D65	x	0,284	0,246	0,220
	y	0,493	0,582	0,637
	Y	44,8	25,2	15,2
	λ_d	541 nm	535 nm	532 nm
	P_e	0,392	0,561	0,660
Illuminant A	x	0,370	0,306	0,265
	y	0,522	0,596	0,645
	Y	39,7	20,9	12,1
	λ_d	535 nm	529 nm	527 nm
	P_e	0,307	0,468	0,576
Notes				
Ionically colored glass				
Bandpass filter				
DIN 58131				
Disclaimer				
All data without tolerances are to be understood to be reference values				



DATA SHEET

SCHOTT VG9



Internal transmittance τ_i at reference thickness
The internal transmittance values, tabulated and graphically represented, are reference values only

λ /nm	τ_i	λ /nm	τ_i	λ /nm	τ_i	λ /nm	τ_i	λ /nm	τ_i	λ /nm	τ_i
200	< 1,0E-05	500	6,130E-01	800	4,315E-02	1100	1,745E-01	2200	8,400E-01	3700	4,100E-01
210	< 1,0E-05	510	6,690E-01	810	4,327E-02	1110	1,824E-01	2250	8,472E-01	3750	4,175E-01
220	< 1,0E-05	520	6,980E-01	820	4,381E-02	1120	1,907E-01	2300	8,548E-01	3800	4,300E-01
230	< 1,0E-05	530	6,980E-01	830	4,462E-02	1130	2,013E-01	2350	8,614E-01	3850	4,420E-01
240	< 1,0E-05	540	6,690E-01	840	4,547E-02	1140	2,079E-01	2400	8,700E-01	3900	4,500E-01
250	< 1,0E-05	550	6,180E-01	850	4,674E-02	1150	2,184E-01	2450	8,736E-01	3950	4,542E-01
260	< 1,0E-05	560	5,520E-01	860	4,781E-02	1160	2,273E-01	2500	8,800E-01	4000	4,524E-01
270	< 1,0E-05	570	4,770E-01	870	4,890E-02	1170	2,372E-01	2550	8,800E-01	4050	4,429E-01
280	< 1,0E-05	580	4,010E-01	880	5,036E-02	1180	2,460E-01	2600	8,840E-01	4100	4,200E-01
290	< 1,0E-05	590	3,300E-01	890	5,300E-02	1190	2,562E-01	2650	8,830E-01	4150	4,015E-01
300	< 1,0E-05	600	2,650E-01	900	5,608E-02	1200	2,644E-01	2700	8,700E-01	4200	3,800E-01
310	< 1,0E-05	610	2,090E-01	910	5,926E-02	1250	3,044E-01	2750	6,870E-01	4250	3,543E-01
320	< 1,000E-05	620	1,640E-01	920	6,255E-02	1300	3,500E-01	2800	6,154E-01	4300	3,223E-01
330	< 1,000E-05	630	1,300E-01	930	6,600E-02	1350	4,000E-01	2850	6,050E-01	4350	2,884E-01
340	< 1,000E-05	640	1,070E-01	940	6,967E-02	1400	4,400E-01	2900	6,000E-01	4400	2,469E-01
350	< 1,000E-05	650	8,900E-02	950	7,392E-02	1450	4,901E-01	2950	5,890E-01	4450	2,054E-01
360	< 1,000E-05	660	7,500E-02	960	7,900E-02	1500	5,300E-01	3000	5,800E-01	4500	1,600E-01
370	< 1,000E-05	670	6,558E-02	970	8,434E-02	1550	5,702E-01	3050	5,626E-01	4550	1,140E-01
380	< 1,000E-05	680	5,811E-02	980	8,972E-02	1600	6,000E-01	3100	5,400E-01	4600	7,450E-02
390	< 1,000E-05	690	5,297E-02	990	9,538E-02	1650	6,371E-01	3150	5,183E-01	4650	5,248E-02
400	< 1,000E-05	700	4,985E-02	1000	1,020E-01	1700	6,700E-01	3200	5,000E-01	4700	3,251E-02
410	7,621E-04	710	4,816E-02	1010	1,091E-01	1750	6,955E-01	3250	4,787E-01	4750	2,203E-02
420	5,715E-03	720	4,695E-02	1020	1,162E-01	1800	7,200E-01	3300	4,600E-01	4800	1,614E-02
430	1,963E-02	730	4,597E-02	1030	1,230E-01	1850	7,407E-01	3350	4,392E-01	4850	1,230E-02
440	5,343E-02	740	4,533E-02	1040	1,295E-01	1900	7,600E-01	3400	4,213E-01	4900	1,000E-02
450	1,170E-01	750	4,479E-02	1050	1,360E-01	1950	7,775E-01	3450	4,118E-01	4950	7,534E-03
460	2,160E-01	760	4,422E-02	1060	1,430E-01	2000	7,900E-01	3500	4,034E-01	5000	5,000E-03
470	3,250E-01	770	4,387E-02	1070	1,510E-01	2050	8,086E-01	3550	4,000E-01	5050	2,773E-03
480	4,290E-01	780	4,354E-02	1080	1,590E-01	2100	8,200E-01	3600	4,000E-01	5100	1,455E-03
490	5,300E-01	790	4,328E-02	1090	1,670E-01	2150	8,312E-01	3650	4,024E-01	5150	6,637E-04

Status 04.10.2018